



DH907 Caspian Oak



DH101 Daintree Oak



DH603 Clouded Ash



DH736 Mountain Oak



DH030 Borough Oak

**deZIGN**  
THE ART OF FLOORING

series  
herringbone.

## TECHNICAL SPECIFICATIONS

SUBJECT	MAIN PARAMETER	SPECS.
<b>GENERAL INFORMATION</b>		
Thickness	2.0 mm	
Wear Layer	Class 32 / 0.40 mm	
Packaging Unit	48 pieces/box = 3.34 m <sup>2</sup>	
Plank Size	609.6 x 114.3 x 2mm	
Application	Moderate Commercial	
Guarantee	20 year residential   5 year commercial	

<b>TECHNICAL DATA</b>		
Name	deZign Series Herringbone	
Type of flooring	Heterogeneous PVC floor covering	ISO 10582
Classification	Class 32 AC 4	ISO 10874
Component	PVC plasticizer Stabilizer CaCO <sub>3</sub>	
Finish	Regular Emboss SEMI-MATT finish.	
Structure	Composite (Wear Layer: 0.40mm; Print film: 0.07mm; Back Layer: 1.63mm)	ISO 24342
Size	Deviation 0.15% of nominal length up to 0.5mm maximum	EN426
Squareness, mm	400mm deviation 0.25; >400mm, 0.35>400mm, 0.35	ISO 24342
Straightness, mm	400mm deviation 0.25; >400mm, 0.35>400mm, 0.35	ISO 24346
Overall thickness, mm	Average: 2.0mm + 0.13/-0.10mm, individual value: average +/- 0.15mm	EN-ISO 24364
Wear layer thickness, mm	0.40mm +13%/ -10%	ISO 24364
Surface treatment	PU coating	
Bevelled edges	Micro-bevel	
Colour Fastness	Minimum 6	ISO 105-B02
Dimensional Stability	0.25%	ISO 23999
Total Mass Per Unit Area	3.444 kg/m <sup>2</sup> + 13% /-10%	ISO 23997
Residual Indentation (average)	0.10 mm	ISO 24343-1
Reaction to fire	Bfl-s1	EN 13501-1
Chemical resistance	Class 0, excellent	ISO 26987
Effect of a castor chair	25 000 cycle no delamination	ISO 4918
Slip Resistance	>R9	DIN 51130
	DS	EN13893
Hardness	60°+/-5°	
Abrasion Resistance	Group T	EN 660-2
Toxicity	Non-toxic, no heavy metals	EN 71-3
Formaldehyde Emission	E1	EN 717-1
Recycled Materials	No	

<b>INSTALLATION &amp; MAINTENANCE GUIDELINES</b>		
Installation	Adhere to manufacturers installation guidelines as set out on packaging.	
Cleaning & Maintenance	Non-abrasive detergent & micro fibre mop	
	Avoid excessive exposure to water	
Caution	Do not expose to direct sunlight	